

# PERFECT COVER®

## VAPOR-PERMEABLE



### DESCRIPTION:

Perfect Cover® Vapor-Permeable has a liquid-tight top layer and a self-adhesive underside, which is suitable for all hard and smooth floors such as: laminate, PVC, tiles, plastic floors and stairs. Ideal for painting, plastering, moving and building. The breathable membrane lets through 0.00172 gallons per sq. ft. per day (70 grams per m<sup>2</sup> per 24 hours), and therefore, it can also be used on wooden floors.

Application: The substrate must remain dry, clean, dust-free, and free from chemical agents. It is advisable to conduct preliminary tests. Lay the rolls with an overlap of approximately 4 inches (10 cm) and press firmly. Processing temperature should be between 41°F and 104°F (5-40 °C). Not suitable for recently laid concrete. The underfloor heating must be switched off.

### APPLICATION

- Hardwood floor
- LVT
- Tile
- Countertops
- Stairs
- Other surfaces

### FEATURES

- Self-adhesive
- Vapor-permeable
- Shock-absorbing
- Moisture resistant
- Reusable
- Anti-slip



### TECHNICAL DATA

Appearance	TL.014	-
Width	TL.013	39.37 in (100 cm)
Weight	TS EN 29073-1	0.476 oz/sq. ft. (160 g/m <sup>2</sup> )
Thickness	TS EN 29073-2	59.06 mils (1.5 mm)
Tensile strength (CD)	TS EN 29073-3	lbf/in 11.42 (N/5cm 100)
Tensile elongation (CD)	TS EN 29073-3	100% (+/- 10%)
Tensile strength (MD)	TS EN 29073-3	lbf/in 11.42 (N/5cm 100)
Tensile elongation (MD)	TS EN 29073-3	80% (+/-20%)
Water vapour permeability	ASTM E398	0.00172 gal/ft <sup>2</sup> /day (70g/m <sup>2</sup> /24h)
Tearing strength (CD)	TS EN ISO 90732-4	2.205 lb (1 kg)
Tearing strength (MD)	TS EN ISO 90732-4	4.41 lb (2 kg)
Peeling at 180	D41 1015	

### MATERIAL

- Material - Non-woven made of 100% PES fibers
- Adhesive - Water-based acrylic
- Color - Blue
- Laminated - Laminated with an impermeable, breathable nonwoven

